



**DATA SHEET**  
**DS 052**  
**Rev. 6 dd 02/12/2014**  
**INEFIL NIMO**

I.N.E. S.p.A.  
Via Facca 10  
35013 Cittadella (PADOVA)  
ITALY  
Tel. : +39 049/9481111 Fax: + 39 049/9400249  
Internet: [www.ine.it](http://www.ine.it) E mail: [ine@ine.it](mailto:ine@ine.it)

**CLASSIFICATION****APPROVALS**

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.28: ER100S-G	EN ISO 16834-A: G 62 3 M21 Mn3Ni1Mo
ASME SFA 5.28: ER100S-G	


**ALLOY TYPE**

Copper-coated solid wire for welding high strength steels.

**APPLICATIONS**

Low-alloy copper-coated solid wire with Ni-Mo additions designed for welding high yield strength steels and with tensile strength higher than 690 MPa. Good impact strength at low temperatures. Suitable for the metal working industry, offshore fabrication, chemical and petrochemical industry. It also has applications in fabrications of HSLA (high-strength low-alloy) steels, which may be used for industrial machinery construction, cranes and other highly stressed structural components. To be used under the shield of Ar+CO<sub>2</sub>.

**MATERIALS TO BE WELDED**

ASTM		EN		Others
A 514	API 5LX X65	10137-2 S460	10208-2 L480	RQT 601
A 517	API 5LX X70	10137-2 S500	10208-2 L550	Navy Q1
HY80	API 5LX X80	10137-2 S550	(BS 4360 Gr 55F)	NAXTRA 70
HY90	API 5A L80	10137-2 S620		WELDOX 700
HY100		10137-2 S690		

**WELDING GUIDELINES**

Preheat and interpass temperature 150°C. PWHT is not required. To obtain the best mechanical properties results, the use with low heat input is advised (follow the steel producer recommendations).

**TECHNICAL INFORMATION**

Gas: Mix Ar- CO<sub>2</sub> (EN 14175)  
Welding position: all positions

**WELDING PARAMETERS**

Current	DC + Reverse polarity				
	0.8	1.0	1.2	1.6	
Diameter (mm)					
Volts (V)	15 ÷ 30	17 ÷ 31	18 ÷ 32	19 ÷ 38	
Intensity (A)	70 ÷ 200	90 ÷ 240	110 ÷ 300	130 ÷ 450	



**DATA SHEET**  
**DS 052**  
**Rev. 6 dd 02/12/2014**  
**INEFIL NIMO**

I.N.E. S.p.A.  
Via Facca 10  
35013 Cittadella (PADOVA)  
ITALY  
Tel. : +39 049/9481111 Fax: + 39 049/9400249  
Internet: [www.ine.it](http://www.ine.it) E mail: [ine@ine.it](mailto:ine@ine.it)

**TYPICAL CHEMICAL COMPOSITION OF WIRE**

C %	Mn %	Si %	S %	P %	Cr %	Ni %	Mo %	Cu %	
0.08	1.50	0.70	0.010	0.010	0.10	1.10	0.40	0.12	

**TYPICAL MECHANICAL PROPERTIES**

GAS		Yield strength	Tensile strength	Elongation on	Impact energy (Charpy V)				
		Rs	Rm	A 5d	+ 20°C	0°C	-20°C	-30°C	-40°C
		(MPa)	(MPa)	%	(Joule)	(Joule)	(Joule)	(Joule)	(Joule)
<b>M21</b>	as welded	680	750	20	120	-	90	70	-

**PRODUCTS AVAILABLE**

Process	Product	Classification AWS	Classification EN
<b>MIG/MAG</b> Solid wire	INEFIL 100	AWS A 5.28: ER100S-1	EN 16834-A: G Mn3Ni1,5Mo
	INEFIL 110	AWS A 5.28: ER110S-1	(EN 16834-A: G Mn3Ni2,5CrMo)
	INEFIL 70	AWS A 5.28: ER100S-G	EN 16834-A: G Mn3NiCrMo
	INEFIL NIMOCR	AWS A 5.28: ER100S-G	EN 16834-A: G M Mn3Ni1CrMo
<b>TIG</b> Rods	INETIG 100	AWS A 5.28: ER100S-1	EN 16834-A: W Mn3Ni1,5Mo
	INETIG 110	AWS A 5.28: ER110S-1	(EN 16834-A: W Mn3Ni2,5CrMo)
<b>SAW</b> Submerged arc	INESUB S3NIMO	AWS A 5.23: EG	EN 26304-A: S3Ni1Mo
	INESUB EF3	AWS A 5.23: EF3	EN 26304-B: SUN2M33
<b>FCAW</b> Cored wire	INETUB M111TG-K3	AWS A 5.28: E110C-K3	EN 18276-A: T 2NiMo
	INETUB M91TG	AWS A 5.28: E90C-G	EN 18276-A: T 55 5 Z M M
	INETUB M121TG-K4	AWS A 5.28: E120C-K4	EN 18276-A: T Mn2NiCrMo
	INETUB B121T5-K4	AWS A 5.29: E121T5-K4	EN 18276-A: T Mn2NiCrMo
<b>SMAW</b> Electrodes	INE 80 B	AWS A 5.5: E10018M	EN 18275-A: E 1NiMo