



DATA SHEET
DS 360
Rev. 5 dd 14/01/2013
INEFIL AL5%SI – 4043

I.N.E. S.p.A.
 Via Facca 10
 35013 Cittadella (PADOVA)
 ITALY
 Tel. : +39 049/9481111 Fax: + 39 049/9400249
 Internet: www.ine.it E mail: ine@ine.it

CLASSIFICATION

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.10: ER4043	EN ISO 18273: S AISi5
AWS A 5.10M: R4043	EN ISO 18273: S Al 4043
ASME SFA 5.10: ER4043	
ASME SFA 5.10M: R4043	

APPROVALS

ALLOY TYPE

4043 for welding aluminum alloy containing 5% silicon.

APPLICATIONS

Solid wire designed for welding aluminum alloys containing 2% maximum of alloy elements and aluminum alloys with a silicon content up to 7%. It finds application in constructions and car fabrication. Excellent characteristics of fluency and penetrations. To be used under the shield of Argon.

MATERIALS TO BE WELDED

ASTM	EN	Others
	(DIN 1725-1: AlMgSi0.5)	EN AW 6060 - AlMgSi0.5
	(DIN 1725-1: AlMgSi0.7)	EN AW 6082 - AlMgSi1
	(DIN 1725-1: AlMgSi0.8)	
	(DIN 1725-2: G-AISi5)	

WELDING GUIDELINES

PWHT is not required.

TECHNICAL INFORMATION

Gas: Argon (EN ISO 14175)
 Welding positions: all positions





DATA SHEET
DS 360
Rev. 5 dd 14/01/2013
INEFIL AL5%SI – 4043

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

TYPICAL CHEMICAL COMPOSITION OF WIRE

Mn %	Si %	Cu %	Cr %	Ti %	Mg %	Zn %	Fe %	Al %	
0.01	5.00	0.02	0.01	0.01	0.01	0.01	0.14	Bal.	

TYPICAL MECHANICAL PROPERTIES

GAS		Yield strength	Tensile strength	Elongation on % 5d
		Rs	Rm	A 5d
		(MPa)	(MPa)	%
I1	as welded	40	150	10

PRODUCTS AVAILABLE

Processo	Prodotto	Classificazione AWS	Classificazione EN
MIG/MAG Solid wire			
TIG Rods	INETIG AL5%SI - 4043	AWS A 5.10: ER4043	EN 18273: S AISi5
SMAW Electrodes			