



DATA SHEET
DS 059
Rev. 7 dd 13/05/2015
INEFIL CROMO 2

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

CLASSIFICATION**APPROVALS**

AWS SPECIFICATIONS	EN SPECIFICATIONS
AWS A 5.28: ER90S-G	EN ISO 21952-A: G CrMo2Si
AWS A 5.28M: ER62S-G	
ASME SFA 5.28: ER90S-G	
ASME SFA 5.28M: ER62S-G	

TÜV		

ALLOY TYPE

2.25Cr-1Mo content to be used for the welding of creep resistant steel.

APPLICATIONS

Low alloy copper-coated solid wire with 2.25% Cr and 1% Mo content to be used for the welding of creep resistant steel. Chemical composition of wire conforming to EN ISO specification. It is used in chemical industry and in the ammonia synthesis process, for heat exchangers, boilers, piping and pressure vessels for temperature service up to about 600°C. It will also find applications in the petro-chemical industries, suitable for facing on casting and for casting repairs. To be used under the shield of Ar+CO₂.

MATERIALS TO BE WELDED

ASTM		EN		Altri
A387 Gr 21&22	A200 T21, T22	10222-2 12CrMo 9 10	(BS 1503 Gr 622)	
A182 F22	A213 T22	10028-2 10CrMo9-10	(BS 1504 Gr 622)	
A217 WC9	A335 P22	(GS-18CrMo9 10)	(BS 3100 Gr B3)	
A234 WP22	A199 T21, T22	(DIN 11CrMo9-10)	(BS 3604 Gr 622)	
		(DIN 6CrMo9 10)	(BS 3059 Gr 622/640)	
		(DIN 12CrMo 9 10)	(BS 3059 Gr 622/490)	
		(BS 1501 Gr 622)		

WELDING GUIDELINES

Preheat and interpass temperature 200 ÷ 300°C. PWHT at 690 ÷ 750°C for an hour.

TECHNICAL INFORMATION

Gas: Mix Ar- CO₂ (EN 14175)
Welding positions: all positions

**WELDING PARAMETERS**

Current	DC + Reverse polarity				
Diameter (mm)	0.8	1.0	1.2	1.6	
Volts (V)	16 ÷ 28	17 ÷ 32	18 ÷ 34	19 ÷ 38	
Intensity (A)	60 ÷ 200	80 ÷ 260	100 ÷ 360	130 ÷ 450	



DATA SHEET
DS 059
Rev. 7 dd 13/05/2015
INEFIL CROMO 2

I.N.E. S.p.A.
Via Facca 10
35013 Cittadella (PADOVA)
ITALY
Tel. : +39 049/9481111 Fax: + 39 049/9400249
Internet: www.ine.it E mail: ine@ine.it

TYPICAL CHEMICAL COMPOSITION OF WIRE

C %	Mn %	Si %	S %	P %	Cr %	Mo %	Cu %		
0.09	1.00	0.60	0.005	0.010	2.60	1.00	0.12		

TYPICAL MECHANICAL PROPERTIES

GAS		Yield strength	Tensile strength	Elongation on % 5d	Impact energy (Charpy V)				
		Rs	Rm	A 5d	+ 20°C	0°C	-20°C	-40°C	-60°C
		(MPa)	(MPa)	%	(Joule)	(Joule)	(Joule)	(Joule)	(Joule)
M21	after PWHT	540	650	23	170	-	-	-	-

PRODUCTS AVAILABLE

Process	Product	Classification AWS	Classification EN
MIG/MAG Solid wire	INEFIL B3	AWS A 5.28: ER90S-B3	EN 21952-B: G 2C1M
	INEFIL B3 L	AWS A 5.28: ER80S-B3L	EN 21952-B: G 2C1ML
TIG Rods	INETIG CROMO 2	AWS A 5.28: ER90S-G	EN 21952-A: W CrMo2Si
	INETIG B3	AWS A 5.28: ER90S-B3	EN 21952-B: W 2C1M
	INETIG B3 L	AWS A 5.28: ER80S-B3L	EN 21952-B: W 2C1ML
SAW Submerged arc	INESUB EB3	AWS A 5.23: EB3	EN 24598-A: S CrMo2
	INESUB EB3R	AWS A 5.23: EB3R	EN 24598-A: S CrMo2
FCAW Cored wire	INETUB B91T5-B3	AWS A 5.29: E91T5-B3	
	INETUB M91TG-B3	AWS A 5.29: E91TG-B3	
	INETUB R91T1-B3	AWS A 5.29: E91T1-B3	
SMAW Electrodes	INE B3	AWS A 5.5: E9018-B3	EN 3580-A: E CrMo2
	INE B3 L	AWS A 5.5: E8018-B3L	EN 3580-A: E CrMo2L